AMENDMENTS TO THE SPECIFICATION:

At page 19, please amend Table 3 as follows:

Experiment No.	Steel Type	TA (MPa)	EL (%)	TSXEL	Residual γ volume (%)	Tempered martensite area (%)	Hole expansion rate (%)	Plating adhesion	Plating appearance	Class
1	A	545	37	20388	9.7	4.7	64	Very good	Very good	Inv. ex.
2	B	566	36	20486	8.5	4.3	60	Good	Very good	Inv. ex.
3	C	579	35	20249	10.4	7.5	61	Very good	Very good	Inv. ex.
4	D	646	33	21319	5.7	4.5	60	Very good	Very good	Inv. ex.
5	E	583	37	21397	9.9	6.2	63	Very good	Very good	Inv. ex.
6	F	608	36	21901	12.5	4.0	62	Good	Very good	Inv. ex.
7	G	602	39	23491	13.9	7.6	64	Very good	Very good	Inv. ex.
8	H	607	32	19658	5.5	9.1	60	Good	Very good	Inv. ex.
9	I	620	36	22351	13.5	6.4	60	Very good	Very good	Inv. ex.
10	J	606	37	22674	11.0	7.0	62	Good	Very good	Inv. ex.
11	K	674	30	20379	10.7	5.4	58	Very good	Very good	Inv. ex.
12	L	659	31	20244	10.2	3.5	58	Very good	Very good	Inv. ex.
13	M	693	30	20570	5.8	5.3	58	Very good	Very good	Inv. ex.
14	N	764	28	21458	13.5	5.6	56	Very good	Very good	Inv. ex.
15	O	609	35	21290	14.4	6.3	60	Very good	Very good	Inv. ex.
16	P	792	29	22637	13.9	6.6	56	Very good	Very good	Inv. ex.
17	Q	504	28	14152	2.5	4.2	55	Very good	Very good	Comp. ex.
18	R	764	20	15390	9.3	10.5	38	Good	Very good	Comp. ex.
19	S	600	22	13209	7.2	5.0	60	Good	Good	Comp. ex.
20	T	494	28	13883	2.4	0.9	55	Very good	Very good	Comp. ex.
21	U	739	20	14887	5.9	10.3	27	Good	Good	Comp. ex.
22	V	487	34	16605	2.6	4.6	62	Very good	Very good	Comp. ex.
23	W	589	30	17825	9.6	6.8	65	Good	Good	Comp. ex.
24	X	510	37	18912	1.6	3.2	68	Good	Good	Comp. ex.
25	Y	670	27	17762	2.4	10.2	51	Good	Good	Comp. ex.

A clean copy of amended Table 3 is provided for the convenience of the Examiner.

Experiment No.	Steel Type	TA (MPa)	EL (%)	TSXEL	Residual γ volume (%)	Tempered martensite area (%)	Hole expansion rate (%)	Plating adhesion	Plating appearance	Class
8	H	607	32	19658	5.5	9.1	60	Good	Very good	Inv. ex.
10	J	606	37	22674	11.0	7.0	62	Good	Very good	Inv. ex.
11	K	674	30	20379	10.7	5.4	58	Very good	Very good	Inv. ex.
12	L	659	31	20244	10.2	3.5	58	Very good	Very good	Inv. ex.
13	M	693	30	20570	5.8	5.3	58	Very good	Very good	Inv. ex.
14	N	764	28	21458	13.5	5.6	56	Very good	Very good	Inv. ex.
15	O	609	35	21290	14.4	6.3	60	Very good	Very good	Inv. ex.
16	P	792	29	22637	13.9	6.6	56	Very good	Very good	Inv. ex.
17	Q	504	28	14152	2.5	4.2	55	Very good	Very good	Comp. ex.
18	R	764	20	15390	9.3	10.5	38	Good	Very good	Comp. ex.
19	S	600	22	13209	7.2	5.0	60	Good	Good	Comp. ex.
20	T	494	28	13883	2.4	0.9	55	Very good	Very good	Comp. ex.
21	U	739	20	14887	5.9	10.3	27	Good	Good	Comp. ex.
22	V	487	34	16605	2.6	4.6	62	Very good	Very good	Comp. ex.
23	W	589	30	17825	9.6	6.8	65	Good	Good	Comp. ex.
24	X	510	37	18912	1.6	3.2	68	Good	Good	Comp. ex.
25	Y	670	27	17762	2.4	10.2	51	Good	Good	Comp. ex.